

Laying instructions

ADVICES

All substrates on which the AGGLOTECH[®] products are installed must be correctly cured, mechanically strong, free from loose parts, grease, oils, fats, waxes or paint. Sizes, thicknesses, cleaning, finishing, damaged parts of the products must be checked before the installation. AGGLOTECH[®] declines any responsibility in case of installation of defective pieces.

TILES

For the installation on cementitious screeds AGGLOTECH[®] suggests a flexible adhesive (Mapei Granirapid or Agglofix[®] Agglotech)

For tiles sizes starting from 60 x 60 cm, a highly-deformable S2 glue (Elastorapid Mapei or Agglofix[®] Agglotech) is recommended (Elastorapid Mapei- Agglofix[®] Agglotech).

The use of the "buttering floating" technique (double spreading) improves the adhesion between product and support. AGGLOTECH[®] suggests to wait 2-3 days after the tile's installation for the grouting of joints, using a specific elastic product. For all information concerning the product used for the laying (adhesive, grouting's mortar etc) consult the producer's technical card.

STAIRS

For the installation of treads AGGLOTECH[®] suggests an highly deformable adhesive in S2 class (Elastorapid Mapei- Agglofix Agglotech)

he use of the "buttering floating" technique (double spreading) improves the adhesion between product and support. AGGLOTECH[®] advises a joint of expansion of at least 1 cm from eventual points of tension. For all information concerning the product used for the laying (adhesive, grouting's mortar etc) consult the producer's technical card.

RISERS

For the risers, that have to be installed as the stairs, AGGLOTECH[®] suggests a thickness of 3 cm.

SKIRTINGS

The installation can be done with the same adhesive used for tiles. Use an elastic product for the grouting.

IMPORTANT NOTES

After the installation it is very important to protect the material fitly! AGGLOTECH[®] declines any responsibility for damaged material after the posing.

OUR TECHNICAL DEPARTMENT IS AT YOUR DISPOSAL FOR ANY FURTHER INFORMATION

AGGLOTECH SPA

Via Monte S. Viola, 16 – 37142 Verona
Tel. +39 045 551777 – Fax +39 045 8701123
www.agglotech.com – info@agglotech.com

Vertriebsbüro Deutschland

AGGLOTECH DEUTSCHLAND GMBH

Eich 2 – 73479 Ellwangen, Deutschland
Tel. +49 7961 568391 – Fax +49 7961 568392
info@agglotech.de – www.agglotech.de